



LL8420A

Linear Low Density Polyethylene Resin

Revised Date: Dec, 2018

Special Characteristics: InnoPlus LL8420A resin is a linear low density polyethylene which is designed for injection molding application. This grade has very narrow molecular weight distribution, offers an excellent impact strength, rigidity, environmental stress cracking resistance and processability.

Typical Applications: InnoPlus LL8420A is recommended for producing general purpose injection molding applications; lids, housewares, trash bins, masterbatch carrier.

Typical Properties:

| Properties | LL8420A | Unit | Test Method |
|--|---------|-------------------|-------------|
| Physical Properties | | | |
| Melt Index (190 °C, 2.16 kg) | 20 | g/10 min | ASTM D1238 |
| Density | 0.924 | g/cm ³ | ASTM D792 |
| Melting Point | 123 | °C | ASTM D3418 |
| Vicat Softening Point | 92 | °C | ASTM D1525 |
| Mechanical Properties (Based on compression specimens) | | | |
| Tensile Strength at Yield | 15 | MPa | ASTM D638 |
| Tensile Strength at Break | 10 | MPa | ASTM D638 |
| Elongation at Break | 700 | % | ASTM D638 |
| 1% Secant Modulus | 310 | MPa | ASTM D638 |
| Durometer Hardness | 53 | Shore D | ASTM D2240 |

Processing Condition:

The recommended temperature setting is in the range of 170 - 190 °C for extruder and 180 - 200 °C for Nozzle.

Note: Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.